
SCOTCH-LANE WET REMOVABLE TAPE SERIES 750

FINAL REPORT



October 17, 2003

Technical Report Documentation Page

1. Report No.	2. Government Accession	No. 3. Recipient's Catalog No.
WI-03-00		
4. Title and Subtitle	•	5. Report Date
SCOTCH-LANE WET REFLECTIVE REMOVABLE TAPE SERIES 750		0 Oct-03
		6. Performing Organization Code
7. Author(s)		Performing Organization Report No.
Debby Kozol, Thomas Notbohm		WI-03-00
9. Performing Organization Name and Address		10. Work Unit No. (TRAIS)
Wisconsin Department of Transportation DTID/BH0/Signs and Marking Implement Section 4802 Sheboygan Ave. Hill Farms Madison, WI 53705		11. Contract or Grant No.
		The solidate of statistics.
12. Sponsoring Agency Name and Address		13. Type of Report and Period Covered
Wisconsin Department of Transportation DTID/BH0/Signs and Marking Implement Section 4802 Sheboygan Ave. Hill Farms Madison, WI 53705		Final Report 2000-2003
		14. Sponsoring Agency Code WisDOT Study PE-00-03
15. Supplementary Notes		
16. Abstract		
Beltline, USH 12, in August 2000 and USThe product was installed and was evaluevaluated for wet night retroreflectivity. I alternatives such as temporary raised pawhere visibility of the temporary marking	SH 151 near I-39/90/Stated at each site for Recommendation is favement marker refle in all weather conditi	truction work zones on the South Madison /94 interchange at Madison in October 2002. r a one- to two-month period. The product was for this product, and/or other wet-reflective ectors, to be considered for use at work zones tions is especially critical. Example locations es, and other tapers on high-speed, high-volume
17. Key Words 18. Dist		18. Distribution Statement
Pavement Marking, Temporary, Tape, Retroreflectivity Safety, Traffic, Reflectivity, Rain		No Restrictions
	<u>i</u>	
19. Security Classification (of this report)	20. Security Classification (d	(of this pa 21. No. of Pages 22. Price
Unclassified	unclassfied	

PE-00-03

Scotch-Lane Wet Reflective Removable Tape Series 750

WisDOT Highway Research Study # PE-00-03

by

THOMAS NOTBOHM DEBBY KOZOL

for

WISCONSIN DEPARTMENT OF TRANSPORTATION
DIVISION OF TRANSPORTATION INFRASTRUCTURE DEVELOPMENT
BUREAU OF HIGHWAY CONSTRUCTION
PAVEMENTS SECTION
TECHNOLOGY ADVANCEMENT UNIT
3502 KINSMAN BLVD., MADISON, WI 53704-2507

October 17, 2003

The Technology Advancement Unit of the Division of Transportation Infrastructure Development, Bureau of Highway Construction, conducts and manages the highway technology advancement program of the Wisconsin Department of Transportation. This publication does not endorse or approve any commercial product even though trade names may be cited, does not necessarily reflect official views or policies of the agency, and does not constitute a standard, specification or regulation.

TABLE OF CONTENTS

<u>SECTION</u> <u>PAGI</u>	<u>₹</u>
Technical Report Documentation Pagei	
Title Pageii	
Table of Contents ii	i
Introduction1	
Objective1	
Evaluation	
Recommendations	
LIST OF PHOTOGRAPHS	
PHOTOGRAPHS	
Figure 1:	
Figure 2:2	
Figure 3:2	

INTRODUCTION

The Wisconsin Department of Transportation (WisDOT) Bureau of Highway Operations decided to evaluate 3M's Scotch-Lane Wet Reflective Removable Tape Series 750 in work zone applications. Results from the temporary installations would determine if the product is acceptable for statewide work zone use.



Figure 1: Close up of Scotch-Lane Tape Series 750

OBJECTIVE

The objective of this study is to determine if this product will provide increased retroreflectivity during rainy and other wet conditions. Traditional pavement marking paints and tapes lose their retroreflective properties when covered with water.

EVALUATION

Barricade Flasher Service on the South Madison Beltline, USH 12, and Project ID 1206-00-71 installed the product on August 23, 2000. The installation was during Stage 1 in mainline shift tapers and ramp tapers at each end of the auxiliary lane construction zone. The product was also installed by Traffic Signing & Marking on USH 151 (E. Washington Ave.) at the I-39/90/94 interchange at Madison, Project ID 1011-01-74. The USH 151 usage was in October 2002 in temporary lane shifts.



Figure 2: Installation

On the Beltline project the contractor noted the tape could not be installed with a machine roller since the tape was too thick from the ripples to be wound tight enough. Instead, the contractor had to unwind the tape and lay it as straight as possible. The contractor reported that the primer used, 3M Brand P-50, wasn't the same that they normally use for removable tape. Manufacturer did not indicate this to be the case.

The tape was viewed during the day during dry conditions. It was viewed several times at night during wet and dry conditions, up to two months after installation.

Both the yellow and white tapes looked excellent at night, in both wet and dry conditions. The tape was clearly brighter than other temporary tape/paint materials in wet conditions. Retroreflectivity readings were not conducted on the WisDOT projects, but were obtained from National Transportation Product Evaluation Program (NTPEP) tests.



Figure 3: Finished Installation

In NTPEP tests, white Series 750 tape had a minimum retroreflectivity of 953 mc/lux/m 2 initially and 405 mc/lux/m 2 after 120 days. Yellow Series 750 had a minimum of 469 mc/lux/m 2 initially and 187 mc/lux/m 2 after 120 days. These readings were under dry conditions.

RECOMMENDATIONS

This product performed better in wet weather than traditional markings. It is our recommendation that this product, and/or other wet-reflective alternatives such as temporary raised pavement marker reflectors, be considered for use where visibility of temporary markings in all weather conditions is especially critical. Examples may include where freeway lanes are shifted across joint lines, and other tapers on high-speed, high-volume roadways.